



Day 1 Practice Session 2 – Lap 6




Day 1 Practice Session 2 – Lap 20



PCC (mbar) Min: 399 Max: 1083 Mean: 581 (dis.) Rate: 20 Hz

| | |
|---------------------|-----------|
| BI_CLUTCHpressure | 0 psi |
| CONTROL_TEMP_LSB | 50 °C |
| IRL_RevLimit_On_LSB | 1 cnt |
| PAB | 1057 mbar |
| PCC | 1014 mbar |
| PF | 1019 kPa |
| PO | 251 kPa |
| POWER_TEMP_LSB | 34 °C |
| PW | 136 kPa |
| SERIAL_STATUS_LED | 0 |
| SW_STAT | 0 |
| TA | 29 °C |
| TF | 28 °C |
| TO | 109 °C |
| TW | 33 °C |
| VB voltage | 13.7 V |

Day 1 Practice Session 1 – Lap 48



BI_CLUTCH:pressure

| | |
|----------------------|-----------|
| CONTROL_TEMP_LSB | 0 psi |
| IRL_RevLimit_Cnt_LSB | No Value |
| PAB | 6 cnt |
| FCC | 1059 mbar |
| PF | 897 mbar |
| PO | 998 kPa |
| POWER_TEMP_LSB | 262 kPa |
| PW | No Value |
| SERIAL_STATUS_LED | 113 kPa |
| SW_STA T | 0 |
| TA | 0 |
| TF | No Value |
| TO | No Value |
| TW | 109 °C |
| VB voltage | No Value |
| | 13.9 V |

CONTROL_TEMP_LSB (°C)

100
90
80
70
60
50
40
30
20
10
0



Herguth Laboratories, Inc.

Certificate of Analysis

Lab Number [REDACTED]

[REDACTED]

08/02/04

Page 1

P.O. Number : [REDACTED]

Client Code : [REDACTED]

Sample Date : 07/20/04

Herguth ID : LAB723531

Oil Code :

Description NEW ALISYN LLOW

| Test Performed | Proc-Rev | Result |
|-------------------------------------|-----------|---------------|
| Flash Point COC, ASTM D92 | 0092-1.4 | 200 Deg. C |
| Flash Point PMCC, ASTM D93 | 0093-1.5 | 166.0 Deg. C |
| Viscosity@40 Deg C, ASTM D445(mod) | 0445A-1.8 | 18.4 cSt |
| Viscosity@100 Deg C, ASTM D445(mod) | | 4.08 cSt |
| Acid Number, ASTM D664(mod) | 1118-3.2 | 0.91 mg KOH/g |
| Metals by ICP, Organic | 1158-3.4 | |
| Iron (Fe) | | <1 ppm |
| Aluminum (Al) | | <1 ppm |
| Chromium (Cr) | | <1 ppm |
| Copper (Cu) | | <1 ppm |
| Lead (Pb) | | <1 ppm |
| Tin (Sn) | | <1 ppm |
| Nickel (Ni) | | 1 ppm |
| Silver (Ag) | | <1 ppm |
| Silicon (Si) | | <1 ppm |
| Sodium (Na) | | <3 ppm |
| Boron (B) | | <8 ppm |
| Zinc (Zn) | | 321 ppm |
| Phosphorus (P) | | 5 ppm |
| Calcium (Ca) | | 1984 ppm |
| Magnesium (Mg) | | 12 ppm |
| Barium (Ba) | | <1 ppm |
| Molybdenum (Mo) | | <1 ppm |
| Potassium (K) | | <5 ppm |
| Strontium (Sr) | | 6 ppm |
| Density @ 15C, ASTM D4052 | 4052-1.6 | 0.8448 g/mL |
| Base Number, ASTM D4739 | 4739-1.2 | 6.74 mg KOH/g |
| Special Project Testing | 9999-1.0 | Comments |

These results are submitted pursuant to our current Terms, Conditions and Limitations and Laboratory Pricing Policy. No responsibility or liability is assumed for the manner in which these results are used or interpreted.

101 Corporate Place, Vallejo, CA 94590-6968 * Toll-Free Phone 1-800-645-5227 * Fax 1-707-554-0109



Herguth Laboratories, Inc.

Certificate of Analysis

Lab Number [REDACTED]

[REDACTED]

12/20/04

Page 1

P.O. Number : [REDACTED]

Client Code : [REDACTED]

Sample Date : 12/07/04

Description : ID: SA016-20

TOTAL MILES: 840.4

AFTER TRACK TIME

| Test Performed | Proc-Rev | Result |
|-------------------------------------|-----------|---------------|
| Viscosity@40 Deg C, ASTM D445(mod) | 0445A-1.8 | 19.0 cSt |
| Viscosity@100 Deg C, ASTM D445(mod) | | 4.01 cSt |
| Density @ 15C, ASTM D4052 | 4052-1.6 | 0.8447 g/mL |
| Base Number, ASTM D4739 | 4739-1.2 | 5.39 mg KOH/g |
| Acid Number, ASTM D664(mod) | 1118-3.2 | 1.86 mg KOH/g |
| Flash Point COC, ASTM D92 | 0092-1.4 | 192 Deg. C |
| Flash Point PMCC, ASTM D93 | 0093-1.5 | 148.0 Deg. C |
| Metals by ICP, Organic | 1158-3.5 | |
| Iron (Fe) | | 30 ppm |
| Aluminum (Al) | | 26 ppm |
| Chromium (Cr) | | 1 ppm |
| Copper (Cu) | | 53 ppm |
| Lead (Pb) | | 35 ppm |
| Tin (Sn) | | 1 ppm |
| Nickel (Ni) | | 9 ppm |
| Silver (Ag) | | <1 ppm |
| Silicon (Si) | | 106 ppm |
| Sodium (Na) | | 42 ppm |
| Boron (B) | | <3 ppm |
| Zinc (Zn) | | 273 ppm |
| Phosphorus (P) | | 21 ppm |
| Calcium (Ca) | | 1557 ppm |
| Magnesium (Mg) | | 5 ppm |
| Barium (Ba) | | 1 ppm |
| Molybdenum (Mo) | | 9 ppm |
| Potassium (K) | | 5 ppm |
| Strontium (Sr) | | 1 ppm |

These results are submitted pursuant to our current Terms, Conditions and Limitations and Laboratory Pricing Policy. No responsibility or liability is assumed for the manner in which these results are used or interpreted.

101 Corporate Place, Vallejo, CA 94590-6968 * Toll-Free Phone 1-800-645-5227 * Fax 1-707-554-0109